



Shenzhen Halnziye Electronics Co.,Ltd

Add:3-4/F Bld.D Hehengxing Sci & Tech Park , No.19 Minqing Road
Longhua District,Shenzhen 518109,China

Tel:0086-755-28772795 Fax:0086-755-28772796 Website:www.halnziye.net

Double Side Thermal Tape Datasheet

Specifications

Items	Units	Test method	Test Result
Color	No	Visual	White
Thermal Conductivity	W/m-K	ASTM D5470	1.6
Thermal Impedance	°C -in ² /W	ASTM D5470	0.52
Fire-protection Rating	UL-94	—	V-0
Specific Gravity	g/cm ³	ASTM D792	2.2
Hardness	Shore OO	ASTM D2240	—
Tensile Strength	Kgf/cm ²	ASTM D412	—
Voltage Bore	Kv/mm	—	—
Thickness	mm	ASTM D347	0.15
Operation Temperature	°C	EN344	-40~120°C
Phase change Temperature	°C	—	—

※ The product temperature, not spontaneous combustion,
mining the general methods can be stored at room temperature